



Mg Partially Stabilized Zirconia

	TBD-MZ3
ZrO ₂ (+HfO ₂)	96.5%.±0.25
MgO	3.5% ±0.1%.
Particle size D50	0.4–0.6um
After granulation particle size D50	20-50um
Specific surface area BET (m ² /g)	8–12
SiO ₂	0.01% max
Al ₂ O ₃	0.01% max
Fe ₂ O ₃	0.01% max
TiO ₂	0.01% max
Ig. loss:	0.1%-0.5%